

# PERFORMANCE GUIDE

IF4072-72W60

# **LSE427 Acrylic Transfer Adhesive**

Version: 1 Date: 9/2025 Approved by: KC

## **Product Description**

IF4072-72W60 is a 2-mil thick film of high-performance acrylic pressure sensitive adhesive. The adhesive is protected by a two-side silicone coated 72# polycoated Kraft liner. This product is designed for applications that require adhesion to low surface energy and other challenging substrates.


#### **Product Construction**

• Carrier: NA

• Adhesive: 2.0 mils LSE427 Acrylic

• Liner: 72# Bleached PCK

• Web Width: 60"



## **Features**

- High performance acrylic adhesive
- Good shear properties
- Moisture stable PCK liner
- Double Liner available

#### **Benefits**

- High initial tack and adhesion to most substrates
- Excellent for uneven or rough surfaces
- Water & Humidity resistant
- Chemical resistant
- Conformable
- Excellent die cutting properties

### **Applications**

- General purpose mounting & bonding applications
- Foam bonding applications
- Decorative Trim
- Nameplate or Faceplate Mounting
- Graphic Mounting Applications
- Mounting to powder coated metals

| IF4072-72W60 Physical Properties |                       |                |        |
|----------------------------------|-----------------------|----------------|--------|
| Thickness                        | Mils                  |                |        |
| Adhesive                         | 2.0                   |                |        |
| Liner                            | 5.3                   |                |        |
| Total Thickness                  | 7.3                   |                |        |
| Performance Test                 | Test Method           | Typical Values |        |
| Loop tack                        | PSTC-16-Method A      | Lbs./in.       | Oz/in. |
| Stainless Steel                  | Backed with 2 mil PET | 8.6            | 137.6  |
| HDPE                             |                       | 3.8            | 60.8   |
| Peel Adhesion 2 mil PET Backed   | PSTC-101-Method A     | Lbs./in.       | Oz/in. |
| 30 minute dwell                  | Stainless Steel       | 8.5            | 136    |
| 24 hour dwell                    | Stainless Steel       | 8.8            | 140.8  |
| 30 minute dwell                  | HDPE                  | 3.6            | 57.6   |
| 24 hour dwell                    | HDPE                  | 4.0            | 64     |
| 30 minute dwell                  | TPO                   | 4.6            | 73.6   |
| 24 hour dwell                    | TPO                   | 4.7            | 75.2   |
| 30 minute dwell                  | PP                    | 5.2            | 83.2   |
| 24 hour dwell                    | PP                    | 7.0            | 112    |
| 30 minute dwell                  | LDPE                  | 3.7            | 59.2   |
| 24 hour dwell                    | LDPE                  | 6.5            | 104    |
| Shear                            | PSTC-107-Method A     | Hours to Fail  |        |
| 1 kg weight                      | 72°F                  | 55+            |        |
|                                  |                       |                |        |

Values given are typical and not for use in specifications

#### **SERVICE TEMPERATURE**

Application: Above 50°F (10°C) for best performance

End Use: -40°F to 350°F (-40°C to 177°C)

#### **APPLICATION DETAILS**

For best performance surfaces must be clean, dry and free of any oil, grease or other contaminant.

#### **SHELF LIFE**

Two year shelf life when stored at 75°F. (24°C.) and 50% relative humidity or less. It is recommended that the product be stored in its original package until ready to use.

CALL 1-800-328-2619 for additional product information

**IMPORTANT NOTICE:** The information given and recommendations made herein are based on our research and are believed to be accurate. In every case, user shall determine before using any product in full scale production, whether such product is suitable for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied. No representative of ours has any authority to waive or change the foregoing provisions unless in a specific agreement signed by the officers of seller and manufacturer. Ultimately, sellers and manufacturers only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.



<sup>™</sup> Trademark of Morgan Adhesives Company LLC

Registered Trademark of Morgan Adhesives Company LLC www.Mactac.com