

TECHNICAL DATA SHEET*



mactac.com

41918

2.0 Mil TC Clear Polypropylene

Description

Product

Face: 2.0 mil TC Clear Polypropylene

Adhesive: BP-52

Liner: 40#

Total Construction

Caliper (Approx): 5.1 mils +/- 10%

Face

A biaxially-oriented film designed for prime label applications. Its acrylic top coat was specifically engineered for flexo ink receptivity.

Physical Properties

Caliper
Elongation at Break, % (YIELD)
Tensile, lbs/in (YIELD)
Opacity

Typical Value

.002 " +/- 10%

Test Method

ASTM D2103
ASTM D1922
ASTM D589
ASTM D882

Adhesive

A general purpose acrylic adhesive with excellent die cutting characteristics and ultimate adhesion to a broad range of substrates. Well suited for small, cylindrical labeling and is glove friendly.

Physical Properties

180° Peel Adhesion
Stainless Steel

Typical Value

4.6 lbs / in

Test Method

PSTC-101A (30 min. applied)

Loop Tack
Stainless Steel

lbs / in

PSTC-16A

Temperature Ranges

Minimum Application Temperature
Service Temperature

40°F (4°C)

-40°F to 200°F (-40°C - 93°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner

A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Physical Properties

Caliper
Basis Weight

Typical Value

0.0025 " +/- 10%

41 lbs. +/- 10%

Test Method

TAPPI T-411

TAPPI T-410

Shelf Life

One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit www.mactac.com