

TECHNICAL DATA SHEET*



41925

SafeTE™ Synthetic

Description

Product

Face: SafeTE™ Synthetic

Adhesive: BP-164

Liner: 40#

Total Construction

Caliper (Approx): **7.2** mils +/- 10%

Face This product is a polyolefin-based, clay-coated film designed to be compatible with most common impact, and many non-impact, print methods. It is waterproof, tear resistant, and resists temperature fluctuations. It is grease resistant. It will die cut and fold easily and is compatible with hot foil stamping and embossing.

Physical Properties

Caliper

Typical Value

.0041 "

Test Method

ASTM D2103

Opacity

90%

ASTM D882

Brightness

TAPPI T-425

Adhesive A general purpose hot melt adhesive with excellent quick-stick properties. This adhesive exhibits excellent adhesion to a broad range of packaging surfaces and has improved die cutting and stripping attributes compared to other hot melt rubber based adhesives.

Physical Properties

180° Peel Adhesion

Stainless Steel

Typical Value

3.9 lbs / in

Test Method

PSTC-101A (30 min. applied)

Loop Tack

Stainless Steel

6.1 lbs / in

PSTC-16A

Temperature Ranges

Minimum Application Temperature

40°F (17°C)

Service Temperature

-50°F to 150°F (-45°C - 65°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner A bleached, calendered liner featuring excellent die cutting and stripping characteristics. Recommended for use in roll-to-roll applications.

Physical Properties

Caliper

Typical Value

.0025 "

Test Method

TAPPI T-411

Basis Weight

41 lbs

TAPPI T-410

Shelf Life One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit **www.mactac.com**