

TECHNICAL DATA SHEET*



42693 3 Mil PrimeScan®

Description

Product

Face: 3 Mil PrimeScan®

Adhesive: SureLock™

Liner: 2.5 Mil

Total Construction

Caliper (Approx): 6.3 mils +/- 10%

Face This product is a polyolefin-based, clay-coated film designed to be compatible with most common impact, and many non-impact, print methods. It is waterproof, tear resistant, grease resistant, and resists temperature fluctuations. It will die cut and fold easily and is compatible with hot foil stamping and embossing.

Physical Properties

Caliper

Typical Value

.003 "

Test Method

ASTM D2103

Opacity

90%

ASTM D882

Brightness

TAPPI T-425

Adhesive A hot melt adhesive exhibiting high tack and appropriate flow to aid in many hard-to-stick textured applications. It converts with less build up on press than many other higher coat weight competitors and also provides a flat release profile for good dispensing.

Physical Properties

180° Peel Adhesion
Stainless Steel

Typical Value

4.4 lbs / in

Test Method

PSTC-101A (30 min. applied)

Loop Tack
Stainless Steel

6.1 lbs / in

PSTC-16A

Temperature Ranges

Minimum Application Temperature
Service Temperature

25°F (-3.8°C)

-50°F to 140 °F (-45°C - 60°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner A bleached, calendered liner featuring higher tensile and tear properties than the 40# liner, making it an excellent liner for perforating, fan-folding, and edge-punching.

Physical Properties

Caliper

Typical Value

.0025 "

Test Method

TAPPI T-411

Basis Weight

41 lbs

TAPPI T-410

Shelf Life One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit **www.mactac.com**