TECHNICAL DATA SHEET*



mactac.com

PJ3802

Vivid[™] 2.6 Mil White Polypropylene

Description

Product

Face: 2.6 Mil White Polypropylene

Adhesive: MP238

Liner: 2.4 SCK

Total Construction

Caliper (Approx): 4.3 mils +/-

Revised: 7/2/2024

0%

Face

This white top-coated, pearlescent biaxially oriented polypropylene is a semi-conformable film designed for excellent printing, converting and label dispensing. Proprietary top coating delivers excellent adhesion for superior graphics and print receptivity for various methods including UV Flexo, Water Flexo, Gravure, UV Inkjet, and Hot Stamp.

Physical Properties	Typical Value	Test Method
Caliper	0.0026 +/- 10%	ASTM D2103
Elongation at Break, % (YIELD)	177 MD 42 CD	ASTM D1922
Tensile, lbs/in (YIELD)	13 MD 27 CD	ASTM D589
Opacity	86	ASTM D882

Adhesive

MP238 is a permanent, emulsion acrylic adhesive with excellent tack and ultimate adhesion to a variety of surfaces. MP238 is designed for film labeling applications. It exhibits exceptional clarity and resistance to water whitening. Has received Association of Plastic Recyclers Design® for Recyclability Recognition on PET containers.

Physical Properties	Typical Value	Test Method
180° Peel Adhesion Stainless Steel	1.5 lbs / in	PSTC-101A (30 min. applied)
HDPE	1.4 lbs / in	PSTC-101A (30 min. applied)
Loop Tack		
Stainless Steel	2.2 lbs / in	PSTC-16A
HDPE	1.4 lbs / in	PSTC-16A
Temperature Ranges		
Minimum Application Temperature Service Temperature	+25°F (-4°C) -40°F to +257° F (-40 to) +125°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner

A super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.pplications.

Physical Properties	Typical Value	Test Method
Caliper	0.0024 " +/- 10%	TAPPI T-411
Basis Weight	39.9 lbs. +/- 10%	TAPPI T-410

Shelf Life One year from the date of shipment, when stored at 72°F and 50% relative humidity.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call 1-800-548-3456 for additional product information or visit www.mactac.com

TM Trademark of Morgan Adhesives Company LLC

^{*}This document represents typical values and is not considered a specification.

Registered Trademark of Morgan Adhesives Company LLC