

PERFORMANCE GUIDE

Represents Typical Values Only

www.mactac.com

PJ7902 Revised: 09/2018 KSH

Vivid™2.6 Mil White Polypropylene

| Description | cription | | Applications and End Uses | |
|-------------|--|---|--|---|
| Product | PJ7902 is a 2.6 mil top coated white biaxially oriented polypropylene (Label-Lyte®) with a quick tack All Temp permanent adhesive and a 2.4 semi-bleached super calendared kraft liner. | | For prime labeling applications requiring the durability and aesthetics of film. Recommended for semi-rigid and rigid containers. Market segments: food packaging and those with cold damp substrates. | |
| Face | This white topcoated pearlescent polypropylene is a semi conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application. | | | |
| | Physical Properties Without Adhesive | | | |
| | Caliper, inches | | +/- 10% | ASTM D2103 |
| | Elongation, % (YIELD) | 12 MD | 45 CD | ASTM D1922 |
| | Tensile, lbs./in. (YIELD) | 14 MD | 80 CD | ASTM D882 |
| | Opacity | 88% | | ASTM D589 |
| | | s including polystyrene, polypropy | | hylene, paper and |
| | corrugate, especially in cold tem Physical Properties of Adhesive | nperatures. Suitable for cold, dam | | hylene, paper and |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches | o.001 +/- 10% | p labeling ap | hylene, paper and pplications. |
| | corrugate, especially in cold tem Physical Properties of Adhesive | nperatures. Suitable for cold, dam 0.001 +/- 10% Corrugate: 2.6 | p labeling ap | hylene, paper and pplications. A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 | PSTC-101/ | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 | PSTC-101/ PSTC-101/ PSTC-101/ | hylene, paper and pplications. A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 HDPE: 2.4 | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 PSTC-16 | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. Loop Tack (1"), lbs./in. Temperature Ranges | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 HDPE: 2.4 Stainless Steel: 5.5 | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) |
| | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. Loop Tack (1"), lbs./in. | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 HDPE: 2.4 | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 PSTC-16 PSTC-16 | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) A (30 min. applied) |
| Liner | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. Loop Tack (1"), lbs./in. Temperature Ranges Minimum Application Service Ranges | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 HDPE: 2.4 Stainless Steel: 5.5 -10°F (-23.33°C) -65°F to +150°F (-54°C to 65.6°C) | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 PSTC-16 PSTC-16 CTM #45 (Polyester | pplications. A (30 min. applied) A (30 min. applied) A (30 min. applied) Curwood |
| Liner | corrugate, especially in cold tem Physical Properties of Adhesive Thickness, inches 180° Peel Adhesion, lbs./in. Loop Tack (1"), lbs./in. Temperature Ranges Minimum Application Service Ranges A super calendared kraft liner excel | 0.001 +/- 10% Corrugate: 2.6 HDPE: 4.9 Stainless Steel: 4.8 Corrugate: 1.9 HDPE: 2.4 Stainless Steel: 5.5 -10°F (-23.33°C) -65°F to +150°F (-54°C to 65.6°C) Ilent for die cutting, stripping and labelis. | PSTC-101/ PSTC-101/ PSTC-101/ PSTC-16 PSTC-16 PSTC-16 CTM #45 (Polyester | hylene, paper and pplications. A (30 min. applied) A (30 min. applied) A (30 min. applied) Curwood |

Shelf Life One year when stored at 72° F and 50% R.H.

Polyfilm® is a registered Trademark of the Morgan Adhesives Company Label-Lyte® is a registered Trademark of the ExxonMobil Company

This product complies with CONEG regulations.

All MACtac Roll Label products meet the requirements of the Clean Air Act of 1990.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most up-to-date version at www.mactac.com

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

™ Trademark of Morgan Adhesives Company.



Registered Trademark of Morgan Adhesives Company.