# **TECHNICAL DATA SHEET\***



mactac.com

## **PJL7702**

# Vivid™ 2.4 Mil White Polypropylene

### Description

**Product** 

Face: 2.4 Mil White Polypropylene

Total Construction Caliper (Approx):

**5.5** mils +/- 10%

Revised: 7/2/2024

Adhesive: CHILL AT FDA

Liner: 2.4 SCK

#### **Face**

This white, top-coated pearlescent polypropylene is a semi-conformable film designed for excellent printing, converting and label dispensing. Print test product and consult with your ink supplier to confirm suitability for your application. Has received Association of Plastic Recyclers Design® for Recyclability Recognition on HDPE and PP containers and PE Flexible packaging.

Physical Properties	Typical Value	<b>Test Method</b>
Caliper	0.0024 " +/- 10%	ASTM D2103
Elongation at Break, % (YIELD)	170 MD 35 CD	ASTM D1922
Tensile, lbs/in (YIELD)	14 MD 29 CD	ASTM D589
Opacity	90	ASTM D882

### Adhesive

Chill AT FDA is an All Temp permanent, rubber-based, direct food contact adhesive that performs well in normal to freezer temperature applications. Chill AT FDA has excellent tack and ultimate adhesion to many surfaces and may be used as the food contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, partial dehydrated and raw fruits and vegetables. Suitable for cold, damp labeling applications. FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b).

Physical Properties	Typical Value	Test Method	
180° Peel Adhesion Stainless Steel	3.6 lbs / in	PSTC-101A (30 min. applied)	
HDPE	2.2 lbs / in	PSTC-101A (30 min. applied)	
Loop Tack			
Stainless Steel	4.7 lbs / in	PSTC-16A	
HDPE	2.8 lbs / in	PSTC-16A	
Temperature Ranges			
Minimum Application Temperature	-10°F (-23°C)		
Service Temperature	-65°F to +150°F (-54°C to +66°C)		
isolaimor: Tostad with 2.6 mil white POPP film facestock at room	tomporature on standard lab r	anals. The service temperature listed is subject	

**Disclaimer:** Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

### Liner

A super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.

Physical Properties	Typical Value	Test Method
Caliper	0.0024 " +/- 10%	TAPPI T-411
Basis Weight	39.9 lbs. +/- 10%	TAPPI T-410

**Shelf Life** One year from the date of shipment, when stored at 72°F and 50% relative humidity.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call 1-800-548-3456 for additional product information or visit www.mactac.com

<sup>\*</sup>This document represents typical values and is not considered a specification.