

TECHNICAL DATA SHEET*

mactac.com

PJN7002

2.0 Mil White Polypropylene EZ Convert Film

Description

Product

Face: 2.0 Mil White Polypropylene

Adhesive: 711VHP

Liner: 2.4 SCK

Total Construction

Caliper (Approx): 5.1 mils +/- 10%

Face

Innovative 2 mil white, top coated, semi-cavitated polypropylene with increased rigidity and resistance to moisture, scuffing, and wrinkling that features excellent high-speed converting. Has received Association of Plastic Recyclers Design® for Recyclability Recognition on HDPE containers.

Physical Properties

Caliper

Typical Value

0.0020 " +/- 10%

Test Method

ASTM D2103

Elongation at Break, % (YIELD)

210 MD 40 CD

ASTM D1922

Tensile, lbs/in (YIELD)

23 MD 58 CD

ASTM D589

Opacity

90

ASTM D882

Adhesive

711VHP is a cold temperature, permanent, rubber-based adhesive with excellent tack and ultimate adhesion to a wide variety of surfaces, including most packaging films. 711VHP may be used as the food contact surface of labels and/or tapes applied to poultry, dry food, and processed, frozen, dried, partial dehydrated and raw fruits and vegetables. FDA approved for direct food contact under 21 CFR Section 175.125(a) and (b).

Physical Properties

180° Peel Adhesion

Typical Value

2.7 lbs / in

Test Method

PSTC-101A (30 min. applied)

Stainless Steel

2.2 lbs / in

PSTC-101A (30 min. applied)

HDPE

Loop Tack

Stainless Steel

4.7 lbs / in

PSTC-16A

HDPE

3.1 lbs / in

PSTC-16A

Temperature Ranges

Minimum Application Temperature

+20°F (-7°C)

Service Temperature

-65°F to +160°F (-54°C to +71°C)

Disclaimer: Tested with 2.6 mil white BOPP film facestock at room temperature on standard lab panels. The service temperature listed is subject to limitations of the facestock and substrate used.

Liner

A super calendared kraft liner excellent for die cutting, stripping and label dispensing. Primarily for roll-to-roll applications.

Physical Properties

Caliper

Typical Value

0.0024 " +/- 10%

Test Method

TAPPI T-411

Basis Weight

39.9 lbs. +/- 10%

TAPPI T-410

Shelf Life

One year from the date of shipment, when stored at 72°F and 50% relative humidity.

*This document represents typical values and is not considered a specification.

The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances please contact your Mactac sales representative to discuss your requirements for recommendations. If this is a printed Technical Data Sheet, it is an uncontrolled document. Please check the Mactac website for the latest, most-up-to-date version. The products discussed herein are sold without any warranty as to merchantability or any other warranty, expressed or implied.

Call **1-800-548-3456** for additional product information or visit **www.mactac.com**