

PERFORMANCE GUIDE

Represents Typical Values Only

Revised: 03/2023 LEL

www.mactac.com

FSC® TT8602 Optiscan® 2C Thermal Transfer

Description			Applications and End Uses		
Product		2 is a premium thermal transfer paper uction with a removable adhesive and a 2.4 semied super calendared kraft liner.		Intended for thermal transfer label applications requiring a removable adhesive. *Compatible with most thermal transfer ribbons designed for coated papers.	
Adhesive	A premium bright white, coated facestock designed for high-speed thermal transfer printing. This smooth, smudge resistant face offers great thermal transfer printing and excellent flexo printing. FSC Certified. Certificate Number: FSC- C161021.				
	Physical Properties Without Adhesive				
	Caliper, inches		0.0029 +/- 10%	6 TAPPI T-411	
	Brightness % Reflectance at 75° angle		87	TAPPI T-452	
	Opacity		87	TAPPI T-426	
	Stiffness		150 MD 100 C	D TAPPI T-543	
	Tear, grams		40 MD 50 CD	TAPPI T-414	
	Tensile, lbs./in.		28 MD 17 CD	TAPPI T-494	
	APPLICATIONS. Physical Properties of Adhesive Thickness, inches Peel Adhesion, lbs./in.	0.0007 +/- 10% Stainless Steel = 0.7 Glass = 0.6 HDPE = 0.6 PVC = 0.8		PSTC-101F (7 days applied)	
	Photographic Activity				
	Test (PAT)	Passes		ISO 18916	
		Passes (CFR) Title 16 (CPSC) F 1500.14(b)(8)	Part	ISO 18916 ASTM D4236	
	Test (PAT)	(CFR) Title 16 (CPSC) F 1500.14(b)(8)			
	Test (PAT) LHAMA * TRA* Temperature Ranges Minimum Application	(CFR) Title 16 (CPSC) F 1500.14(b)(8) 16 CFR 1500.3(b)(5), (+25° F (-4°C) on most	7)- (9) FHSA	ASTM D4236 C.R.C., c. 931 sec. (10) & (11) CTM #45 Curwood	
Liner	Test (PAT) LHAMA * TRA* Temperature Ranges Minimum Application Service Ranges	(CFR) Title 16 (CPSC) F 1500.14(b)(8) 16 CFR 1500.3(b)(5), (+25° F (-4°C) on most -40 to +200° F (-40 to	7)- (9) FHSA : surfaces +93°C)	ASTM D4236 C.R.C., c. 931 sec. (10) & (11) CTM #45 Curwood Polyester Film Dry Surface	
Liner	Test (PAT) LHAMA * TRA* Temperature Ranges Minimum Application	(CFR) Title 16 (CPSC) F 1500.14(b)(8) 16 CFR 1500.3(b)(5), (+25° F (-4°C) on most -40 to +200° F (-40 to d kraft liner excellent fo	7)- (9) FHSA : surfaces +93°C)	ASTM D4236 C.R.C., c. 931 sec. (10) & (11) CTM #45 Curwood Polyester Film Dry Surface	
Liner	Test (PAT) LHAMA * TRA* Temperature Ranges Minimum Application Service Ranges A semi-bleached super calendare	(CFR) Title 16 (CPSC) F 1500.14(b)(8) 16 CFR 1500.3(b)(5), (+25° F (-4°C) on most -40 to +200° F (-40 to d kraft liner excellent fo	7)- (9) FHSA : surfaces +93°C)	ASTM D4236 C.R.C., c. 931 sec. (10) & (11) CTM #45 Curwood Polyester Film Dry Surface pping and label dispensing.	

Optiscan is a registered trademark of Morgan Adhesives Company

One year when stored at 72° F and 50% R.H.

Shelf Life

Note: The user is responsible for determining the product's suitability for all aspects of the application. If there are any questions about applications, or regulatory compliances, please contact your MACtac sales representative to discuss your requirements for recommendations. If this is a printed Performance Guide, it is an uncontrolled document. Please check the MACtac website for the latest, most-up-to-date version.

IMPORTANT NOTICE: The information given, and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

 $^{\text{TM}}$ Trademark of Morgan Adhesives Company.

Registered Trademark of Morgan Adhesives Company.

